


Canson Infinity Papers with Epson HDX Inks – Print Permanence Ratings¹




The print permanence data given here are based on tests with samples printed with an Epson SureColor P9000 printer and Epson UltraChrome HDX 11-color pigment inks. Canson Infinity fine art papers, fine art canvas, and photo papers are supplied by Canson SAS, 67, Rue Louis et Laurent Seguin, CS 70139, 07104 Annonay, Cedex, France. Canson Infinity papers are available from suppliers and dealers in countries throughout the world. www.cansoninfinity.com

Display Permanence Ratings and Album/Dark Storage Permanence Ratings (Years Before Noticeable Fading and/or Changes in Color Balance Occur) ²								
Photo Papers, Fine Art Papers, and Canvas Printed With Epson UltraChrome HDX inks	Displayed Prints Framed Under Glass ⁽³⁾	Displayed Prints Framed With UV Filter ⁽⁴⁾	Displayed Prints Not Framed (Bare-Bulb) ⁽⁵⁾	Album/Dark Storage Rating at 73°F & 50% RH (incl. Paper Yellowing) ⁽⁶⁾	Unprotected Resistance to Ozone ⁽⁷⁾	Resistance to High Humidity ⁽⁸⁾	Resistance to Water ⁽⁹⁾	Are Optical Brighteners Present? ⁽¹⁰⁾
Canson Infinity PrintMaKing Rag	136 years	345 years	77 years	>200 years	>100 years	very high	moderate ⁽¹¹⁾	no
Canson Infinity Edition Etching Rag	115 years	258 years	63 years	>200 years	>100 years	very high	moderate ⁽¹¹⁾	no
Canson Infinity Velin Museum Rag	138 years	314 years	73 years	>200 years	>100 years	very high	moderate ⁽¹¹⁾	no
Canson Infinity Rag Photographique	116 years	253 years	64 years	>200 years	>100 years	very high	moderate ⁽¹¹⁾	no
Canson Infinity Baryta Photographique	115 years	240 years	64 years	>200 years	>100 years	very high	moderate ⁽¹¹⁾	no
Canson Infinity Baryta Prestige	106 years	215 years	58 years	>200 years	>100 years	very high	moderate ⁽¹¹⁾	no
Canson Infinity Platine Fibre Rag	96 years	215 years	51 years	>200 years	>100 years	very high	moderate ⁽¹¹⁾	no
Canson Infinity Aquarelle Rag	132 years	347 years	68 years	>200 years	>100 years	very high	moderate ⁽¹¹⁾	no
Canson Infinity Photo Luster Premium RC	127 years	241 years	72 years	>200 years	>100 years	very high	high	yes

©2020 by Wilhelm Imaging Research, Inc. As long as this document remains complete and unaltered, it may be freely distributed to your associates, customers, and organizations. This PDF report may also be reproduced in magazine articles, books, and other hardcopy print publications; however, it may not be posted on websites without written permission. Links to <www.wilhelm-research.com> are welcome. Wilhelm Imaging Research, Inc., Box 775, Grinnell, Iowa 50112 U.S.A.

Canson Infinity Papers with Canon LUCIA PRO Inks – Print Permanence Ratings¹




The print permanence data given here are based on tests with samples printed with a Canon 12-ink imagePROGRAF PRO-1000 printer with Canon LUCIA PRO pigment inks with LUCIA PRO Chroma Optimizer clear ink. Canon LUCIA PRO inks and the inkjet head used in the PRO-1000 are also used in the Canon PRO-2000, PRO-4000, and PRO-6000 printers and the print permanence ratings given here are expected to be similar with these printers. www.cansoninfinity.com

Display Permanence Ratings and Album/Dark Storage Permanence Ratings (Years Before Noticeable Fading and/or Changes in Color Balance Occur) ²								
Photo Papers, Fine Art Papers, and Canvas Printed with Canon LUCIA PRO Pigment Inks	Displayed Prints Framed Under Glass ⁽³⁾	Displayed Prints Framed With UV Filter ⁽⁴⁾	Displayed Prints Not Framed (Bare-Bulb) ⁽⁵⁾	Album/Dark Storage Rating at 73°F & 50% RH (incl. Paper Yellowing) ⁽⁶⁾	Unprotected Resistance to Ozone ⁽⁷⁾	Resistance to High Humidity ⁽⁸⁾	Resistance to Water ⁽⁹⁾	Are Optical Brighteners Present? ⁽¹⁰⁾
Canson Infinity PrintMaKing Rag	72 years	153 years	39 years	>200 years	> 100 years	very high	moderate ⁽¹¹⁾	no
Canson Infinity Edition Etching Rag	60 years	124 years	33 years	>200 years	> 100 years	very high	moderate ⁽¹¹⁾	no
Canson Infinity Velin Museum Rag	78 years	166 years	41 years	>200 years	> 100 years	very high	moderate ⁽¹¹⁾	no
Canson Infinity Rag Photographique	60 years	130 years	31 years	>200 years	> 100 years	very high	moderate ⁽¹¹⁾	no
Canson Infinity Baryta Photographique	43 years	88 years	25 years	>200 years	> 100 years	very high	moderate ⁽¹¹⁾	no
Canson Infinity Baryta Prestige	44 years	88 years	28 years	>200 years	> 100 years	very high	moderate ⁽¹¹⁾	no
Canson Infinity Platine Fibre Rag	37 years	80 years	20 years	>200 years	> 100 years	very high	moderate ⁽¹¹⁾	no
Canson Infinity Aquarelle Rag	86 years	188 years	50 years	>200 years	> 100 years	very high	moderate ⁽¹¹⁾	no
Canson Infinity Photo Luster Premium RC	49 years	92 years	26 years	>200 years	> 100 years	very high	high	yes

©2020 by Wilhelm Imaging Research, Inc. As long as this document remains complete and unaltered, it may be freely distributed to your associates, customers, and organizations. This PDF report may also be reproduced in magazine articles, books, and other hardcopy print publications; however, it may not be posted on websites without written permission. Links to <www.wilhelm-research.com> are welcome. Wilhelm Imaging Research, Inc., Box 775, Grinnell, Iowa 50112 U.S.A.

See page 3 for Canson Infinity print permanence data with HP Vivera pigment inks and page 4 for previous-generation Epson UltraChrome K3 inks..

Canson Infinity Papers with HP Vivera Inks – Print Permanence Ratings¹




The print permanence data given here are based on tests with samples printed with HP DesignJet Z3100 and Z3200 printers with HP Vivera 12-color pigment inks, and with HP DesignJet Z6200 printers. Canson Infinity fine art papers, fine art canvas, and photo papers are supplied by Canson SAS, CS 70139, 07104 Annonay, Cedex, France. Canson Infinity papers are available from suppliers and dealers in countries throughout the world.
www.cansoninfinity.com

Display Permanence Ratings and Album/Dark Storage Permanence Ratings (Years Before Noticeable Fading and/or Changes in Color Balance Occur) ²								
Photo Papers, Fine Art Papers, and Canvas Printed with HP Vivera Pigment Inks	Displayed Prints Framed Under Glass ⁽³⁾	Displayed Prints Framed With UV Filter ⁽⁴⁾	Displayed Prints Not Framed (Bare-Bulb) ⁽⁵⁾	Album/Dark Storage Rating at 73°F & 50% RH (incl. Paper Yellowing) ⁽⁶⁾	Unprotected Resistance to Ozone ⁽⁷⁾	Resistance to High Humidity ⁽⁸⁾	Resistance to Water ⁽⁹⁾	Are Optical Brighteners Present? ⁽¹⁰⁾
Canson Infinity PrintMaKing Rag	199 years	361 years	83 years	>300 years	> 100 years	very high	moderate ⁽¹¹⁾	no
Canson Infinity Edition Etching Rag	235 years	370 years	88 years	>300 years	> 100 years	very high	moderate ⁽¹¹⁾	no
Canson Infinity Velin Museum Rag	218 years	360 years	90 years	>300 years	> 100 years	very high	moderate ⁽¹¹⁾	no
Canson Infinity Rag Photographique	219 years	384 years	85 years	>300 years	> 100 years	very high	moderate ⁽¹¹⁾	no
Canson Infinity Rag Photographique DUO	246 years	434 years	87 years	>300 years	> 100 years	very high	moderate ⁽¹¹⁾	no
Canson Infinity Baryta Photographique	160 years	392 years	56 years	>300 years	> 100 years	very high	moderate ⁽¹¹⁾	no
Canson Infinity Platine Fibre Rag	117 years	318 years	39 years	>300 years	> 100 years	very high	moderate ⁽¹¹⁾	no
Canson Infinity Aquarelle Rag	228 years	417 years	90 years	>300 years	> 100 years	very high	moderate ⁽¹¹⁾	no
Canson Infinity Photo High Gloss Premium RC	156 years	390 years	57 years	>300 years	> 100 years	very high	high	yes
Canson Infinity PhotoGloss Premium RC	222 years	453 years	70 years	>300 years	> 100 years	very high	high	yes
Canson Infinity PhotoSatin Premium RC	220 years	442 years	68 years	>300 years	> 100 years	very high	high	yes

©2020 by Wilhelm Imaging Research, Inc. As long as this document remains complete and unaltered, it may be freely distributed to your associates, customers, and organizations. This PDF report may also be reproduced in magazine articles, books, and other hardcopy print publications; however, it may not be posted on websites without written permission. Links to <www.wilhelm-research.com> are welcome. Wilhelm Imaging Research, Inc., Box 775, Grinnell, Iowa 50112 U.S.A.

See page 4 for Canson Infinity print permanence data with previous-generation Epson UltraChrome K3 inks, and page 5 for older-generation Canon LUCIA 12-color inks.

Canson Infinity Papers with Epson K3 Inks – Print Permanence Ratings¹



The print permanence data given here are based on tests with samples printed with an Epson Stylus Pro 9880 printer and Epson UltraChrome K3 with Vivid Magenta pigment inks. Canson Infinity fine art papers, fine art canvas, and photo papers are supplied by Canson SAS, CS 70139, 07104 Annonay, Cedex, France. Canson Infinity papers are available from suppliers and dealers in countries throughout the world.

www.cansoninfinity.com

Display Permanence Ratings and Album/Dark Storage Permanence Ratings (Years Before Noticeable Fading and/or Changes in Color Balance Occur) ²								
Paper, Canvas, or Fine Art Media Printed With Epson UltraChrome K3 Pigment Inks	Displayed Prints Framed Under Glass ⁽³⁾	Displayed Prints Framed With UV Filter ⁽⁴⁾	Displayed Prints Not Framed (Bare-Bulb) ⁽⁵⁾	Album/Dark Storage Rating at 73°F & 50% RH (incl. Paper Yellowing) ⁽⁶⁾	Unprotected Resistance to Ozone ⁽⁷⁾	Resistance to High Humidity ⁽⁸⁾	Resistance to Water ⁽⁹⁾	Are Optical Brighteners Present? ⁽¹⁰⁾
Canson Infinity PrintMaKing Rag	72 years	140 years	39 years	>300 years	>100 years	very high	moderate ⁽¹¹⁾	no
Canson Infinity Edition Etching Rag	69 years	132 years	36 years	>300 years	>100 years	very high	moderate ⁽¹¹⁾	no
Canson Infinity Velin Museum Rag	67 years	129 years	39 years	>300 years	>100 years	very high	moderate ⁽¹¹⁾	no
Canson Infinity Rag Photographique	69 years	125 years	36 years	>300 years	>100 years	very high	moderate ⁽¹¹⁾	no
Canson Infinity Rag Photographique DUO	65 years	123 years	37 years	>300 years	>100 years	very high	moderate ⁽¹¹⁾	no
Canson Infinity Baryta Photographique	45 years	99 years	28 years	>300 years	>100 years	very high	moderate ⁽¹¹⁾	no
Canson Infinity Platine Fibre Rag	53 years	113 years	32 years	>300 years	>100 years	very high	moderate ⁽¹¹⁾	no
Canson Infinity Photo High Gloss Premium RC	60 years	104 years	36 years	>300 years	>100 years	very high	high	yes
Canson Infinity PhotoGloss Premium RC	87 years	145 years	49 years	>300 years	>100 years	very high	high	yes
Canson Infinity PhotoSatin Premium RC	88 years	147 years	48 years	>300 years	>100 years	very high	high	yes
Canson Infinity Aquarelle Rag	67 years	129 years	36 years	>300 years	>100 years	very high	moderate ⁽¹¹⁾	no

©2020 by Wilhelm Imaging Research, Inc. As long as this document remains complete and unaltered, it may be freely distributed to your associates, customers, and organizations. This PDF report may also be reproduced in magazine articles, books, and other hardcopy print publications; however, it may not be posted on websites without written permission. Links to <www.wilhelm-research.com> are welcome. Wilhelm Imaging Research, Inc., Box 775, Grinnell, Iowa 50112 U.S.A.

See page 5 for Canson Infinity print permanence data with older-generation Canon LUCIA 12-color pigment inks.

Canson Infinity Papers with Older Canon Inks – Print Permanence Ratings¹



The print permanence data given here are based on tests with samples printed with a Canon imagePROGRAF iPF5100 and Canon LUCIA 12-color pigment inks. Canson Infinity fine art papers, fine art canvas, and photo papers are supplied by Canson SAS, CS 70139, 07104 Annonay, Cedex, France. Canson Infinity papers are available from suppliers and dealers in countries throughout the world.

www.cansoninfinity.com

Display Permanence Ratings and Album/Dark Storage Permanence Ratings (Years Before Noticeable Fading and/or Changes in Color Balance Occur) ²								
Paper, Canvas, or Fine Art Media Printed With Older Canon LUCIA Pigment Inks	Displayed Prints Framed Under Glass ⁽³⁾	Displayed Prints Framed With UV Filter ⁽⁴⁾	Displayed Prints Not Framed (Bare-Bulb) ⁽⁵⁾	Album/Dark Storage Rating at 73°F & 50% RH (incl. Paper Yellowing) ⁽⁶⁾	Unprotected Resistance to Ozone ⁽⁷⁾	Resistance to High Humidity ⁽⁸⁾	Resistance to Water ⁽⁹⁾	Are Optical Brighteners Present? ⁽¹⁰⁾
Canson Infinity PrintMaKing Rag	116 years	212 years	59 years	>300 years	>100 years	very high	moderate ⁽¹¹⁾	no
Canson Infinity Edition Etching Rag	96 years	199 years	57 years	>300 years	>100 years	very high	moderate ⁽¹¹⁾	no
Canson Infinity Velin Museum Rag	119 years	226 years	61 years	>300 years	>100 years	very high	moderate ⁽¹¹⁾	no
Canson Infinity Rag Photographique	108 years	199 years	56 years	>300 years	>100 years	very high	moderate ⁽¹¹⁾	no
Canson Infinity Rag Photographique DUO	104 years	198 years	54 years	>300 years	>100 years	very high	moderate ⁽¹¹⁾	no
Canson Infinity Baryta Photographique	69 years	146 years	39 years	>300 years	>100 years	very high	moderate ⁽¹¹⁾	no
Canson Infinity Platine Fibre Rag	73 years	130 years	41 years	>300 years	>100 years	very high	moderate ⁽¹¹⁾	no
Canson Infinity Photo High Gloss Premium RC	106 years	175 years	60 years	>300 years	>100 years	very high	high	yes
Canson Infinity PhotoGloss Premium RC	122 years	185 years	69 years	>300 years	>100 years	very high	high	yes
Canson Infinity PhotoSatin Premium RC	116 years	191 years	64 years	>300 years	>100 years	very high	high	yes
Canson Infinity Aquarelle Rag	128 years	238 years	65 years	>300 years	>100 years	very high	moderate ⁽¹¹⁾	no

©2020 by Wilhelm Imaging Research, Inc. As long as this document remains complete and unaltered, it may be freely distributed to your associates, customers, and organizations. This PDF report may also be reproduced in magazine articles, books, and other hardcopy print publications; however, it may not be posted on websites without written permission. Links to <www.wilhelm-research.com> are welcome. Wilhelm Imaging Research, Inc., Box 775, Grinnell, Iowa 50112 U.S.A.

Canson Infinity Inkjet Papers – Print Permanence Ratings¹

Notes on These Tests:

1) The image permanence data presented here are based on tests done with samples printed with the following printers: Epson SureColor P9000 with Epson UltraChrome HDX 11-color pigment inks; Canon imagePROGRAF PRO-1000 printer with LUCIA PRO 12-color pigment inks with Canon LUCIA Chroma Optimizer clear ink; HP DesignJet Z3200 with HP Vivera 12-color pigment inks, including HP Gloss Enhancer clear ink and an HP DesignJet Z6200 with HP Vivera 8-color pigment inks; Epson Stylus Pro 9880 and Epson UltraChrome K3 with Vivid Magenta 10-color pigment inks; and Canon imagePROGRAF iPF5100 with Canon LUCIA 12-color pigment inks. Canson Infinity fine art papers, fine art canvas, and photo papers are supplied by Canson SAS, CS 70139, 07104 Annonay, Cedex, France. Canson Infinity papers are available from suppliers and dealers in countries throughout the world. www.cansoninfinity.com.

These tests were conducted in accordance with long-standing Wilhelm Imaging Research, Inc. test methods, lighting, temperature and relative humidity assumptions, and used the WIR 3.0 Visually-Weighted Fading, Color Imbalance, and D-min (Paper White) Stain Endpoint Criteria. This report is based on multiple Wilhelm Imaging Research print permanence studies conducted over the past ten years (since 2008) commissioned by Canson in France. Even though the papers have the same brand names, papers tested in previous years may have different permanence behaviors than do current papers marketed under these same names. Canson SAS, 67, Rue Louis et Laurent Seguin, CS 70139, 07104 Annonay, Cedex, France.

2) There are currently no ISO or ANSI “Specification” standards which provide a means of making “lifetime” or “noticeable change” predictions for the permanence of inkjet or other digitally-printed photographs under a standardized set of display and storage conditions (display illumination levels, spectral power distribution, ambient temperature, relative humidity, and indoor ozone concentrations) together with image-change criteria and limits (endpoints) for fading, changes in color balance, and d-min or paper white stain formation.

As a long-standing member of the ISO/TC42 WG-5/TG-3 (ISO Technical Committee 42, Working Group 5, Task Group 3) print permanence standards group, WIR is actively involved in the development of new ISO standards for evaluating the permanence of digital prints. However, after more than 40 years of effort that began in 1978 by the ANSI and ISO groups charged with developing a consumer-oriented “Specification Standard” for indoor display and storage of photographs – work on such a standard has been abandoned because of an ongoing lack of agreement among members on the selection of appropriate fading, color balance, and d-min stain endpoint criteria, and on environmental assumptions (including average daily light exposure). It is uncertain when – if ever

Table 1. “Standard” Home Display Illumination Levels Used by Printer, Ink, and Photo Paper Manufacturers

120 lux/12 hrs/day	450 lux or 500 lux/10 hrs/day or 12 hrs/day
Kodak Alaris (for Kodak silver-halide papers and Kodak dye-sub prints)	HP
	Epson
	Canon
	Fuji
	ChromaLuxe
	Ilford
	Canson
	DNP Konica
	Kodak (for Kodak consumer inkjet prints)
	Ferrania
	InteliCoat
	Somerset
	Harman
	LexJet
	Lyson
Luminos	
Hahnemuhle	
Premier Imaging Products	
American Inkjet	
MediaStreet	

– an ISO “Specification Standard” will be published. ISO (International Organization for Standardization), headquartered in Geneva Switzerland, is a consensus-driven organization with fourteen country members. ISO has no enforcement capability to address misuse or abuse of its standards.

The WIR Display Permanence Ratings (DPR) given here are based on accelerated light stability tests conducted at 25 klux with glass-filtered cool white fluorescent illumination with the sample plane air temperature maintained at 24°C and 60% relative humidity. Data were extrapolated to a display condition of 450 lux for 12 hours per day using the Wilhelm Imaging Research, Inc. “Visually-Weighted Endpoint Criteria Set v3.0.” and represent the years of display for easily noticeable fading, changes in color balance, and/or staining to occur. See: Henry Wilhelm, “How Long Will They Last? An Overview of the Light-Fading Stability of Inkjet Prints and Traditional Color Photographs,” *IS&T’s 12th International*

. . . . continues next page

Canson Infinity Inkjet Papers – Print Permanence Ratings¹

Notes on These Tests (continued from previous page):

Table 2. Filtration Conditions Used by Printer, Ink, and Paper Manufacturers with CW Fluorescent Illumination

UV Filter	Glass Filter
Kodak Alaris (for Kodak silver-halide papers and Kodak dye-sub prints)	Hewlett-Packard
	Epson
	Canon
	Fuji
	ChromaLuxe
	Ilford
	Canson
	DNP Konica
	Kodak (for Kodak consumer inkjet prints)
	Ferrania
	InteliCoat
	Somerset
	Harman
	LexJet
	Lyson
	Luminos
	Hahnemuhle
Premier Imaging Products	
American Inkjet	
MediaStreet	

Symposium on Photofinishing Technologies, sponsored by the Society for Imaging Science and Technology, Orlando, Florida, February 2002. This paper may be downloaded in PDF form at no charge from: http://www.wilhelm-research.com/pdf/is_t/WIR_ISTpaper_2002_02_HW.pdf.

For a study of endpoint criteria correlation with human observers, see: Yoshihiko Shibahara, Makoto Machida, Hideyasu Ishibashi, and Hiroshi Ishizuka, "Endpoint Criteria for Print Life Estimation," *Final Program and Proceedings: IS&T's NIP20 International Conference on Digital Printing Technologies*, pp. 673–679, sponsored by the Society for Imaging Science and Technology, Salt Lake City, Utah, November 2004.

See also: Henry Wilhelm, "A Review of Accelerated Test Methods for Predicting the Image Life of Digitally-Printed Photographs – Part II," *Final Program and Proceedings: IS&T's NIP20 International Conference on Digital Printing Technologies*, pp. 664–669, sponsored by the Society for Imaging Science and Technology, Salt Lake City, Utah, November 2004. Also available, with *color illustrations*: www.wilhelm-research.com <WIR_IST_2004_11_HW.pdf>. High-intensity light fading reciprocity failures in these tests are assumed to be zero. Illumination conditions in homes, offices, museums, and galleries do vary, however, and color images will last longer when displayed under lower light levels; likewise, the life of prints will be shortened when displayed under illumination that is more intense than 450 lux. Ink and paper combinations that have not reached a fading or color balance failure point after the equivalent of 100 years of display are given a rating of "more than 100 years" until such time as meaningful dark stability data are available (see discussion in No. 5 below).

Eastman Kodak licensed WIR image permanence data for the Kodak line of consumer inkjet printers, and WIR data for these printers was posted on the WIR website (see, for example, <http://www.wilhelm-research.com/kodak/esp9.html>) WIR's tests with the Kodak consumer inkjet printers are performed using the exact same methodologies employed for all other inkjet printers and other print products posted on the WIR website.

Kodak's internally-developed print permanence test methodologies have been used by the company for many years and the company continues to base its home display-life calculations for Kodak silver-halide (chromogenic) color papers and Kodak dye-sub (thermal dye transfer) prints on 120 lux/12 hours per day, rather than the 450 lux/12 hours per day adopted by WIR. It is important to understand this and other differences between WIR's test methods and Kodak's test methods (see, for example, the article by Charlie Brewer titled "At Least For Ink Jet Print Permanence, WIR and Kodak Mend Fences," *The Hard Copy Supplies Journal*, Lyra Research, Newtonville, MA 02460, March 2008, pp. 1–2. The article is available for download at http://www.wilhelm-research.com/hc/Kodak-WIR_Permanence2008_03.pdf). Some of Kodak's display-life predictions for the now-obsolete Kodak Ultima Picture Paper (a swellable inkjet paper designed for dye-based inks) were *almost 15X* longer than the predictions obtained in the more conservative tests conducted by WIR for this ink/media combination, and can be accounted for by differences in the two test methodologies. For example, Kodak uses 80 klux UV-filtered cool white fluorescent illumination; WIR uses 25 klux glass-filtered cool white fluorescent illumination.

Kodak uses a starting density for fading measurements of only 1.0; WIR uses starting densities of both 0.6 and 1.0. Kodak uses the "ISO Illustrative" endpoint criteria set; WIR uses the visually-weighted WIR Endpoint Criteria Set v3.0. Kodak's display environment light exposure assumption for calculating display life is 120 tereid); WIR uses 450 lux for 12 hours per day (glass filtered). Kodak maintains

. . . continues next page

Canson Infinity Inkjet Papers – Print Permanence Ratings¹

Notes on These Tests (continued from previous page):

50% RH in their accelerated tests; WIR uses 60% RH. Key aspects of Kodak's test methodology and assumptions for calculation of "years of display" are also very different from those used by most other manufacturers of printers, inks, and media. The display lux level assumption of 120 lux (see Table 1) alone makes Kodak's display-life predictions 3.75X greater than the display-life predictions provided by other manufacturers and by WIR.

With many ink/media combinations, Kodak's use of a UV filter instead of the glass filter used by other companies in accelerated light fading tests (see Table 2) further increases Kodak's display-life predictions. For a description of the Kodak tests, see: D. E. Bugner, C. E. Romano, G. A. Campbell, M. M. Oakland, R. J. Kapusniak, L. L. Aquino, and K. E. Maskasky, "The Technology Behind the New KODAK Ultima Picture Paper – Beautiful Inkjet Prints that Last for Over 100 Years," *Final Program and Advanced Printing of Paper Summaries – IS&T's 13th International Symposium on Photofinishing Technology*, pp. 38–43, Las Vegas, Nevada, February 8, 2004. Together with Kodak's own test data, the articles also include light stability data for Kodak Ultima Picture Paper obtained from ongoing tests conducted by the Image Permanence Institute at the Rochester Institute of Technology (Rochester, New York), and from Torrey Pines Research (Torrey Pines, California). The tests were conducted using the Kodak test procedures and included the use of a UV filter with cool white fluorescent illumination; the Image Permanence Institute and Torrey Pines Research also based print-life calculations on 120 lux for 12 hours per day.

- 3) In typical indoor situations, the "Displayed Prints Framed Under Glass" test condition is considered the single most important of the three display conditions listed. *All* prints intended for long-term display should be framed under glass or plastic to protect them from staining, image discoloration, and other deterioration caused by prolonged exposure to cigarette smoke, cooking fumes, insect residues, and other airborne contaminants; this precaution applies to traditional silver-halide black-and-white and color photographs, as well as inkjet, dye-sub, and other types of digital prints.
- 4) Displayed prints framed with ultraviolet filtering glass or ultraviolet filtering plastic sheet generally last longer than those framed under ordinary glass. How much longer depends upon the specific print material and the spectral composition of the illuminate, with some ink/paper combinations benefitting a great deal more than others. Some products may even show reduced life when framed under a UV filter because one of the image dyes or pigments is disproportionately protected from fading caused by UV radiation and this can result in more rapid

changes in color balance than occur with the glass-filtered and/or the bare-bulb illumination conditions. For example, if a UV filter protects the cyan and magenta inks much more than it protects the yellow ink in a particular ink/media combination, the color balance of the image may shift toward blue more rapidly than it does when a glass filter is used (in which case the fading rates of the cyan, magenta, and yellow dyes or pigments are more balanced in the neutral scale). Keep in mind, however, that the major cause of fading with most digital and traditional color prints in indoor display conditions is visible light and although a UV filter may slow fading, it will not stop it. For the display permanence data reported here, Acrylite OP-3 acrylic sheet, a "museum quality" UV filter supplied by Cyro Industries, was used.

- 5) Illumination from bare-bulb fluorescent lamps (with no glass or plastic sheet between the lamps and prints) contains significant UV emissions at 313nm and 365nm which, with most print materials, increases the rate of fading compared with fluorescent illumination filtered by ordinary glass (which absorbs UV radiation with wavelengths below about 330nm). Some print materials are affected greatly by UV radiation in the 313–365nm region, and others very little.

"Gas fading" is another potential problem when prints are displayed unframed, such as when they are attached to kitchen refrigerator doors with magnets, pinned to office walls, or displayed inside of fluorescent illuminated glass display cases in schools, stores, and offices. Field experience has shown that, as a class of media, microporous "instant dry" papers used with dye-based inkjet inks can be very vulnerable to gas fading when displayed unframed and/or stored exposed to the open atmosphere where even very low levels of ozone and certain other air pollutants are present. Resistance to ozone exposure varies considerably, depending on the specific type and brand of dye-based inks and photo paper. In some locations, displayed unframed prints made with certain types of microporous papers and dye-based inks have suffered from extremely rapid image deterioration. This type of premature ink fading is not caused by exposure to light. Polluted outdoor air is the source of most ozone found indoors in homes, offices and public buildings. Ozone can also be generated indoors by electrical equipment such as electrostatic air filters ("electronic dust precipitators") that may be part of heating and air conditioning systems in homes, office buildings, restaurants, and other public buildings to remove dust, tobacco smoke, etc. Electrostatic air filtration units are also supplied as small "tabletop" devices.

Potentially harmful pollutants may be found in combustion products from gas stoves; in addition, microscopic droplets of cooking oil and grease in cooking fumes can damage unframed prints. Because of the wide range of environ-

... continues next page

Canson Infinity Inkjet Papers – Print Permanence Ratings¹

Notes on These Tests (continued from previous page):

mental conditions in which prints may be displayed or stored, the data given here will be limited by the “Unprotected Resistance to Ozone” ratings. That is, when ozone resistance tests are complete, in cases where the “Unprotected Resistance to Ozone” predictions are less than the “Display Permanence Ratings” for displayed prints that are NOT framed under glass (or plastic), and are therefore exposed to circulating ambient air, the “Display Permanence Ratings” will be reduced to the same number of years given for “Unprotected Resistance to Ozone” even though the “Display Permanence Rating” for unframed prints displayed in ozone-free air is higher. For all of the reasons cited above, all prints made with microporous papers and dye-based inks should always be displayed framed under glass or plastic. For that matter, ALL displayed prints, regardless of the technology with which they are made, should be framed under glass or plastic sheets. This includes silver-halide black-and-white and color prints, dye-sub prints, and inkjet prints made with dye-based or pigmented inks on swellable or microporous papers, canvas, or other materials.

6) Prints stored in the dark may suffer slow deterioration that is manifested in yellowing of the print paper, image fading, changes in color balance, and physical embrittlement, cracking, and/or delamination of the image layer. These types of deterioration may affect the paper support, the image layer, or both. Each type of print material (ink/paper combination) has its own intrinsic dark storage stability characteristics; some are far more stable than others. Rates of deterioration are influenced by temperature and relative humidity; high temperatures and/or high relative humidity exacerbate the problems. Long-term dark storage stability is determined using Arrhenius accelerated dark storage stability tests that employ a series of elevated temperatures (e.g., 57°C, 64°C, 71°C, and 78°C) at a constant relative humidity of 50% RH to permit extrapolation to ambient room temperatures (or other conditions such those found in sub-zero, humidity-controlled cold storage preservation facilities). Because many types of inkjet inks, especially those employing pigments instead of dyes, are exceedingly stable when stored in the dark, the eventual life of prints made with these inks may be limited by the instability of the paper support, and not by the inks themselves. Due to this concern, as a matter of policy, Wilhelm Imaging Research does not provide a Display Permanence Rating of greater than 100 years for any inkjet or other photographic print material unless it has also been evaluated with Arrhenius dark storage tests and the data indicate that the print can indeed last longer than 100 years without noticeable deterioration when stored at 73°F (23°C) and 50% RH. Arrhenius dark storage data are also necessary to assess the physical and image stability of a print material when it is stored in an album, portfolio box, or

other dark place. The Arrhenius data given here are only applicable when prints are protected from the open atmosphere; that is, they are stored in closed boxes, placed in albums within protective plastic sleeves, or framed under glass or high-quality acrylic sheet. If prints are stored, displayed without glass or plastic, or otherwise exposed to the open atmosphere, low-level air pollutants may cause significant paper yellowing within a relatively short period of time. Note that these Arrhenius dark storage data are for storage at 50% RH; depending on the specific type of paper and ink, storage at higher relative humidities (e.g., 70% RH) could produce significantly higher rates of paper yellowing and/or other types of physical deterioration.

7) Tests for “Unprotected Resistance to Ozone” are conducted with an accelerated ozone exposure test using a SATRA/Hampden Test Equipment Ltd. Model 903 Automatic Ozone Test Cabinet (with the test chamber maintained at 23°C and 50% RH) and the reporting method outlined in: Kazuhiko Kitamura, Yasuhiro Oki, Hidemasa Kanada, and Hiroko Hayashi (Seiko Epson), “A Study of Fading Property Indoors Without Glass Frame from an Ozone Accelerated Test,” *Final Program and Proceedings – IS&T’s NIP19: International Conference on Digital Printing Technologies*, sponsored by the Society for Imaging Science and Technology, New Orleans, Louisiana, September 28 – October 3, 2003, pp. 415–419.

WIR test methods for ozone resistance are described in: Henry Wilhelm, Kabenla Armah, Dmitriy Shklyarov, Barbara Stahl, and Dimitar Tasev, “A Study of ‘Unprotected Ozone Resistance’ of Photographs Made with Inkjet and Other Digital Printing Technologies,” *Proceedings: Imaging Conference JAPAN 2007, The 99th Annual Conference of the Imaging Society of Japan*, June 6–8, 2007, pp. 137–140. See also: Michael Berger and Henry Wilhelm, “Evaluating the Ozone Resistance of Inkjet Prints: Comparisons Between Two Types of Accelerated Ozone Tests and Ambient Air Exposure in a Home,” *Final Program and Proceedings: IS&T’s NIP20 International Conference on Digital Printing Technologies*, pp. 740–745, sponsored by the Society for Imaging Science and Technology, Salt Lake City, Utah, November 2004. The IS&T article is also available in PDF format from <www.wilhelm-research.com> <WIR_IST_2004_11_MB_HW.pdf>.

8) Changes in image color and density, and/or image diffusion (“image bleeding”), that may take place over time when prints are stored and/or displayed in conditions of high relative humidity are evaluated using a humidity-fastness test maintained at 86°F (30°C) and 80% RH. Depending on the particular ink/media combination, slow humidity-induced changes may occur at much lower humidities – even at 50–60% RH. Test methods for resistance to high humidity and related test

. . . continues next page

Canson Infinity Inkjet Papers – Print Permanence Ratings¹

Notes on These Tests (continued from previous page):

methods for evaluating “short-term color drift” in inkjet prints have been under development since 1996 by Mark McCormick-Goodhart and Henry Wilhelm at Wilhelm Imaging Research, Inc. See: Mark McCormick-Goodhart and Henry Wilhelm, “New Test Methods for Evaluating the Humidity-Fastness of Inkjet Prints,” *Proceedings of “Japan Hardcopy 2005” – The Annual Conference of the Imaging Society of Japan*, Tokyo, Japan, June 9, 2005, pp. 95–98. Available in PDF format from <www.wilhelm-research.com> <WIR_JapanHardcopy2005MMG_HW.pdf>

See also, Henry Wilhelm and Mark McCormick-Goodhart, “An Overview of the Permanence of Inkjet Prints Compared with Traditional Color Prints,” *Final Program and Proceedings – IS&T’s Eleventh International Symposium on Photofinishing Technologies*, sponsored by the Society for Imaging Science and Technology, Las Vegas, Nevada, January 30 – February 1, 2000, pp. 34–39. See also: Mark McCormick-Goodhart and Henry Wilhelm, “Humidity-Induced Color Changes and Ink Migration Effects in Inkjet Photographs in Real-World Environmental Conditions,” *Final Program and Proceedings – IS&T’s NIP16: International Conference on Digital Printing Technologies*, sponsored by the Society for Imaging Science and Technologies, Vancouver, B.C., Canada, October 15–20, 2000, pp. 74–77.

See also: Mark McCormick-Goodhart and Henry Wilhelm, “The Influence of Relative Humidity on Short-Term Color Drift in Inkjet Prints,” *Final Program and Proceedings – IS&T’s NIP17: International Conference on Digital Printing Technologies*, sponsored by the Society for Imaging Science and Technology, Ft. Lauderdale, Florida, September 30 – October 5, 2001, pp. 179–185; and: Mark McCormick-Goodhart and Henry Wilhelm, “The Correlation of Line Quality Degradation With Color Changes in Inkjet Prints Exposed to High Relative Humidity,” *Final Program and Proceedings – IS&T’s NIP19: International Conference on Digital Printing Technologies*, sponsored by the Society for Imaging Science and Technology, New Orleans, Louisiana, September 28 – October 3, 2003, pp. 420–425.

9) Data from waterfastness tests are reported in terms of three subjective classes: “high,” “moderate,” and “low.” Both “water drip” tests and “standing water droplets/gentle wipe” tests are employed. See also: Henry Wilhelm (Wilhelm Imaging Research, Inc.); Richard Adams (Ryerson University); Ken Boydston (MegaVision, Inc.); and Charles Wilhelm (Wilhelm Imaging Research, Inc.): “Improved Water-Resistance Test Methods Utilizing a Multispectral Imaging System to Quantify Black and Color Ink Bleeding for Plain Paper Office and Legal Documents Printed With Pigment- and Dye-Based Inkjet Inks,” *Technical Program and Proceedings: IS&T NIP33: The 33rd International Conference on Digital Printing Technologies and IS&T Digital Printing for Fabrication 2017*, Denver, Colorado; November 5–9, 2017.

10) Optical Brightening Agents (OBAs) [also called “UV brighteners”] are colorless dyes added to the image-side coatings of many inkjet papers – and nearly all “plain papers” – to make them appear whiter and “brighter” than they really are. Optical Brightening Agents absorb ultraviolet (UV) radiation, causing the brighteners to fluoresce (emit light) in the visible region, especially in the blue portion of the spectrum. Fluorescent brighteners can lose activity – partially or completely – as a result of exposure to light. Brighteners may also lose activity when subjected to high temperatures in accelerated thermal aging tests and, it may be assumed, in long-term storage in albums or other dark places under normal room temperature conditions. With loss of brightener activity, papers will appear to have yellowed and to be “less bright” and “less white.” In recent years, traditional chromogenic (“silver-halide”) color photographic papers have been made with UV-absorbing interlayers and overcoats and this prevents brighteners that might be present in the base paper from being activated by UV radiation. It is the relative UV component in the viewing illumination that determines the perceived “brightening effect” produced by fluorescent brighteners. If the illumination contains no UV radiation (for example, if a UV filter is used in framing a print), fluorescent brighteners are not activated and, comparatively speaking, the paper appears to be somewhat yellowed – and not as “white.” This spectral dependency of fluorescent brighteners makes papers containing such brighteners look different depending on the illumination conditions. For example, prints displayed near windows are illuminated with direct or indirect daylight, which contains a relatively high UV component, and if an inkjet paper contains brighteners, this causes the brighteners to strongly fluoresce. When the same print is displayed under incandescent tungsten illumination, which has a low UV component, the brighteners have little effect. Another potential drawback of brighteners is that brightener degradation products may themselves be a source of yellowish stain. These problems can be avoided by not adding fluorescent brighteners to inkjet photographic papers during manufacture. When long-term image permanence is of critical importance – with museum fine art collections, for example – papers with fluorescent brighteners should be avoided where possible.

11) Although the waterfastness of the color image itself is very high with this paper, the absorbent paper base itself may become cockled, curled, and physically distorted after contact with water. For this reason, the waterfastness of this paper/ink combination is listed as “moderate.”