

# Epson DURABrite Pigment Inks and Epson Photo Paper vs. Store-Brand and Other Non-Genuine, Third-Party Inks and Photo Papers – WIR Print Permanence Ratings<sup>1</sup>



An Epson Stylus C88+ printer with high-stability Epson DURABrite Ultra pigment inks with a group of the store-brand and other non-genuine, third-party inks tested in this study.

**Epson DURABrite Ultra Ink System:** Four inks. Epson DURABrite Ultra pigmented Cyan, Magenta, Yellow, and Black. Four individual Epson ink cartridges (the piezo inkjet heads are a permanent part of the printer). Maximum resolution: up to 5760 x 1440 dpi (dots per inch).

Thirteen different store-brand and other third-party, non-genuine inks obtained from countries in eight geographic regions were included in this study. Most of the third-party products included in these tests substituted low-stability, dye-based inks for the high-stability pigments used by Epson in DURABrite and DURABrite Ultra ink formulations.

Users of Epson DURABrite ink printers should be aware that these and most other third-party, non-genuine (“compatible”) inks supplied by others have extremely poor overall permanence and have also very poor water resistance on plain paper. These tests showed that the display permanence ratings of genuine Epson DURABrite ink is from 10 to 500 times greater than the non-genuine store brand and third-party inks. The unprotected ozone resistance of DURABrite ink is from 100 to 1,000 times greater than the non-genuine store brand, and third-party inks.



Epson Premium Glossy Photo Paper with a group of the store-brand and other non-genuine, third-party photo papers tested with the same-brand, of non-genuine, third-party inks.

Display Permanence Ratings and Album/Dark Storage Permanence Ratings (Years Before Noticeable Fading and/or Changes in Color Balance Occur) <sup>2</sup>								
Epson DURABrite and Third-Party Inks And Papers That They Were Printed On	Displayed Prints Framed Under Glass <sup>(3)</sup>	Displayed Prints Framed With UV Filter <sup>(4)</sup>	Displayed Prints Not Framed (Bare-Bulb) <sup>(5)</sup>	Album/Dark Storage Rating at 73°F & 50% RH (incl. Paper Yellowing) <sup>(6)</sup>	Unprotected Resistance to Ozone <sup>(7)</sup>	Resistance to High Humidity <sup>(8)</sup>	Resistance to Water <sup>(9)</sup>	Are UV Brighteners Present? <sup>(10)</sup>
<b>Epson DURABrite Ultra ink cartridges printed on Epson Premium Presentation Matte Paper and Epson Matte Paper Heavyweight</b> (Epson Ink Cartridges T060120, T060220, T060320, T060420)	<b>105 years</b>	185 years	54 years	185 years	> 100 years	high	moderate	yes
<b>Epson DURABrite Ultra ink cartridges printed on Epson Premium Glossy Photo Paper</b> (Epson Ink Cartridges T060120, T060220, T060320, T060420)	<b>40 years</b>	61 years	28 years	>300 years	> 100 years	high	high	no
Office Depot ink cartridges (USA) printed on Office Depot Professional Photo Paper (Office Depot Ink Cartridges for Epson T0441, T0442, T0443, T0444)	<b>0.8 years</b>	0.8 years	0.7 years	now in test	0.3 year	now in test	now in test	yes

©2007 by Wilhelm Imaging Research, Inc. As long as this document remains complete and unaltered, it may be freely distributed to your associates, customers, and friends. This PDF may also be reproduced in magazine articles, books, and other hardcopy print publications; however, it may not be posted on websites without written permission. Links to <www.wilhelm-research.com> are welcomed. Address e-mail inquiries to: <info@wilhelm-research.com> Wilhelm Imaging Research, Inc., Box 775, Grinnell, Iowa 50112 U.S.A.

## Epson DURABrite Pigment Inks and Epson Photo Paper vs. Store-Brand and Other Non-Genuine, Third-Party Inks and Photo Papers – WIR Print Permanence Ratings<sup>1</sup>

Display Permanence Ratings and Album/Dark Storage Permanence Ratings (Years Before Noticeable Fading and/or Changes in Color Balance Occur) <sup>2</sup>								
Epson DURABrite and Third-Party Inks And Papers That They Were Printed On	Displayed Prints Framed Under Glass <sup>(3)</sup>	Displayed Prints Framed With UV Filter <sup>(4)</sup>	Displayed Prints Not Framed (Bare-Bulb) <sup>(5)</sup>	Album/Dark Storage Rating at 73°F & 50% RH (incl. Paper Yellowing) <sup>(6)</sup>	Unprotected Resistance to Ozone <sup>(7)</sup>	Resistance to High Humidity <sup>(8)</sup>	Resistance to Water <sup>(9)</sup>	Are UV Brighteners Present? <sup>(10)</sup>
Calidad "Pigment" ink cartridges (Australia) printed on Calidad Inkjet Glossy Photo Paper (Calidad Ink Cartridges for Epson T0631, T0632, T0633, T0634)	<b>0.6 years</b>	0.6 years	0.4 years	now in test	0.3 year	now in test	now in test	yes
Inkrite ink cartridges (Europe) printed on Inkrite Glossy Photo Paper (Inkrite Ink Cartridges for Epson T0611, T0612, T0613, T0614)	<b>1.9 years</b>	2.1 years	1.1 years	now in test	0.1 year	now in test	now in test	yes
Guang Zhou Yuan se ink (China) printed on Yang fan nai Ink Jet Color Paper (Guang Zhou Yuan se Cartridges for T0631, T0632, T0633, T0634)	<b>0.2 years</b>	0.2 years	0.2 years	now in test	0.3 year	now in test	now in test	yes
Sui-e+ ink (China) printed on Yang fan nai Ink Jet Color Paper (Sui-e+ Bulk ink for Epson T0631, T0632, T0633, T0634)	<b>0.4 years</b>	0.4 years	0.4 years	now in test	0.4 year	now in test	now in test	yes
Certtone ink cartridges (Europe) printed on Certtone Papier Photographique (Certtone Ink Cartridges for Epson T0611, T0612, T0613, T0614)	<b>2.1 years</b>	2.2 years	1.3 years	now in test	0.1 year	now in test	now in test	yes
OfficeMax ink cartridges (USA) printed on OfficeMax Professional Photo Paper, Glossy (OfficeMax Ink Cartridges for T060120, T060220, T060320, T060420)	<b>1.5 years</b>	1.4 years	1.3 years	now in test	0.1 year	now in test	now in test	yes
Comax ink cartridges (Thailand) printed on IJ Photolike Glossy Impression Paper (Comax Ink Cartridges for Epson T0631, T0632, T0633, T0634)	<b>3.9 years</b>	4.7 years	2.6 years	now in test	0.3 year	now in test	now in test	yes
Esyink ink cartridges (Malaysia) printed on GOGI Glossy Photo Paper (Esyink Ink Cartridges for Epson T0631, T0632, T0633, T0634)	<b>0.4 years</b>	0.4 years	0.4 years	now in test	0.1 year	now in test	now in test	yes
Sepoms ink (Singapore/Taiwan) printed on Sepoms Super Glossy Photo Paper (Sepoms Bulk Ink for Epson T0631, T0632, T0633, T0634)	<b>0.8 years</b>	0.9 years	0.5 years	now in test	1.1 year	now in test	now in test	yes
InkStation ink cartridges (Singapore) printed on InkStation Photo Paper (InkStation Bulk Ink for Epson T0631, T0632, T0633, T0634)	<b>1.9 years</b>	1.1 years	0.9 years	now in test	0.2 year	now in test	now in test	yes
G&G ink cartridges (Latin America) printed on Avery Zweckform Premium Glossy Inkjet (C&G Ink Cartridges for Epson T0631, T0632, T0633, T0634)	<b>3.1 years</b>	3.7 years	1.8 years	now in test	0.4 year	now in test	now in test	yes
New Jet ink cartridges (Latin America) printed on Husares Papel Fotografica Calidad Premium (New Jet Ink Cartridges for Epson T0631, T0632, T0633, T0634)	<b>1.5 years</b>	1.6 years	1.1 years	now in test	0.1 year	now in test	now in test	yes

. . . continues next page

# Epson DURABrite Pigment Inks and Epson Photo Paper vs. Store-Brand and Other Non-Genuine, Third-Party Inks and Photo Papers – WIR Print Permanence Ratings<sup>1</sup>

## Permanence Comparison of Epson DURABrite Inks with Non-Genuine Calidad Inks and Photo Paper

Equivalent years of exposure to light in home display at 450 lux for 12 hours per day in an accelerated light stability test (print framed under glass, 24°C and 60% RH) with Epson DURABrite Ultra pigment inks and Epson Premium Glossy Photo Paper printed with an Epson Stylus C87/C88 inkjet printer. The Epson inks and paper have a WIR Display Permanence Rating of 40 years.



Original Print

2 Years

Equivalent years of exposure to light in home display at 450 lux for 12 hours per day in an accelerated light stability test (print framed under glass, 24°C and 60% RH) with third-party Calidad brand "pigment" inks and Calidad Inkjet Glossy Photo Paper printed with an Epson Stylus C87/C88 inkjet printer. The Calidad inks have extremely poor light stability, with a WIR Display Permanence Rating of less than 1 year.



Equivalent years of ambient ozone exposure in an accelerated unprotected ozone resistance test (5 ppm ozone, 23°C and 50% RH) with Epson DURABrite Ultra pigment inks and Epson Premium Glossy Photo Paper printed with an Epson Stylus C87/C88 inkjet printer.



Original Print

1 Year

5 Years

10 Years

25 Years

50 Years

Equivalent years of ambient ozone exposure in an accelerated unprotected ozone resistance test with third-party Calidad brand "pigment" inks and Calidad Inkjet Glossy Photo Paper printed with an Epson Stylus C87/C88 inkjet printer. The Calidad inks and paper were purchased in Australia in February 2007.

# Epson DURABrite Pigment Inks and Epson Photo Paper vs. Store-Brand and Other Non-Genuine, Third-Party Inks and Photo Papers – WIR Print Permanence Ratings<sup>1</sup>

## Notes on These Tests:

1) The image permanence data presented here are based on tests done with Epson DURABrite Ultra inks printed on Epson Premium Glossy Photo Paper. In addition, a variety of store label and other third-party, non-genuine inks and papers were tested. All test samples were printed on Epson Stylus Color C86, D68, C87, and C88+ printers.

2) Display Permanence Ratings (DPR) are based on accelerated light stability tests conducted at 35 klux with glass-filtered cool white fluorescent illumination with the sample plane air temperature maintained at 24°C and 60% relative humidity. Data were extrapolated to a display condition of 450 lux for 12 hours per day using the Wilhelm Imaging Research, Inc. "Visually-Weighted Endpoint Criteria Set v3.0." and represent the years of display for easily noticeable fading, changes in color balance, and/or staining to occur. See: Henry Wilhelm, "How Long Will They Last? An Overview of the Light-Fading Stability of Inkjet Prints and Traditional Color Photographs," *IS&T's 12th International Symposium on Photofinishing Technologies*, sponsored by the Society for Imaging Science and Technology, Orlando, Florida, February 2002: <[www.wilhelm-research.com](http://www.wilhelm-research.com)> <[Wilhelm\\_IS&T\\_Paper\\_Feb\\_2002.pdf](#)>. For a study of endpoint criteria correlation with human observers, see: Yoshihiko Shibahara, Makoto Machida, Hideyasu Ishibashi, and Hiroshi Ishizuka, "Endpoint Criteria for Print Life Estimation," *Final Program and Proceedings: IS&T's NIP20 International Conference on Digital Printing Technologies*, pp. 673–679, sponsored by the Society for Imaging Science and Technology, Salt Lake City, Utah, November 2004.

See also: Henry Wilhelm, "A Review of Accelerated Test Methods for Predicting the Image Life of Digitally-Printed Photographs – Part II," *Final Program and Proceedings: IS&T's NIP20 International Conference on Digital Printing Technologies*, pp. 664–669, sponsored by the Society for Imaging Science and Technology, Salt Lake City, Utah, November 2004. Also available, with *color illustrations*: <[www.wilhelm-research.com](http://www.wilhelm-research.com)> <[WIR IST\\_2004\\_11\\_HW.pdf](#)>. High-intensity light fading reciprocity failures in these tests are assumed to be zero. Illumination conditions in homes, offices, museums, and galleries do vary, however, and color images will last longer when displayed under lower light levels; likewise, the life of prints will be shortened when displayed under illumination that is more intense than 450 lux. Ink and paper combinations that have not reached a fading or color balance failure point after the equivalent of 100 years of display are given a rating of "more than 100 years" until such time as meaningful dark stability data are available (see discussion in No. 6 below).

**Table 1. "Standard" Home Display Illumination Levels Used by Printer, Ink, and Photo Paper Manufacturers**

120 lux/12 hrs/day	450 lux or 500 lux/10 hrs/day or 12 hrs/day
	Fuji
	Hewlett-Packard
	Epson
	Canon
	Lexmark
	Ilford
	Konica Minolta
	Agfa-Gevaert
Kodak	DuPont
	Ferrania
	InteliCoat
	Somerset
	Arches
	LexJet
	Lyson
	Luminos
	Hahnemuhle
	Premier Imaging Products
	American Inkjet
	MediaStreet

Eastman Kodak bases its home display-life calculations on 120 lux/12 hours per day, rather than 450 lux/12 hours per day. Some of Kodak's display-life predictions for Kodak Ultima Picture Paper are *almost 15X* longer than the predictions obtained in the more conservative tests conducted by WIR for this ink/media combination, and can be accounted for by differences in the two test methodologies. For example, Kodak uses 80 klux UV-filtered cool white fluorescent illumination; WIR uses 35 klux glass-filtered cool white fluorescent illumination. Kodak uses a starting density for fading measurements of only 1.0; WIR uses starting densities of both 0.6 and 1.0. Kodak uses the "ISO Illustrative" endpoint criteria set; WIR uses the visually-weighted WIR Endpoint Criteria Set

. . . continues next page

# Epson DURABrite Pigment Inks and Epson Photo Paper vs. Store-Brand and Other Non-Genuine, Third-Party Inks and Photo Papers – WIR Print Permanence Ratings<sup>1</sup>

## Notes on These Tests (continued from previous page):

**Table 2. Filtration Conditions Used by Printer, Ink, and Paper Manufacturers with CW Fluorescent Illumination**

UV Filter	Glass Filter
Kodak	Fuji
	Hewlett-Packard
	Epson
	Canon
	Lexmark
	Ilford
	Agfa-Gevaert
	Konica Minolta
	DuPont
	Ferrania
	InteliCoat
	Somerset
	Arches
	LexJet
	Lyson
	Luminos
	Hahnemuhle
	Premier Imaging Products
American Inkjet	
MediaStreet	

v3.0. Kodak's display environment light exposure assumption for calculating display life is 120 lux for 12 hours per day (UV filtered); WIR uses 450 lux for 12 hours per day (glass filtered). Kodak maintains 50% RH in their accelerated tests; WIR uses 60% RH. Key aspects of Kodak's test methodology and assumptions for calculation of "years of display" are also very different from those used by most other manufacturers of printers, inks, and media. The display lux level assumption of 120 lux (see Table 1) alone makes Kodak's display-life pre-

dictions 3.75X greater than the display-life predictions provided by other manufacturers and by WIR. With many ink/media combinations, Kodak's use of a UV filter instead of the glass filter used by other companies in accelerated light fading tests (see Table 2) further increases Kodak's display-life predictions. For a description of the Kodak tests, see: D. E. Bugner, C. E. Romano, G. A. Campbell, M. M. Oakland, R. J. Kapusniak, L. L. Aquino, and K. E. Maskasky, "The Technology Behind the New KODAK Ultima Picture Paper – Beautiful Inkjet Prints that Last for Over 100 Years," *Final Program and Advanced Printing of Paper Summaries – IS&T's 13th International Symposium on Photofinishing Technology*, pp. 38–43, Las Vegas, Nevada, February 8, 2004. See also: D. E. Bugner, C. E. Romano, G. A. Campbell, M. M. Oakland, R. J. Kapusniak, L. L. Aquino, and K. E. Maskasky, *The Technology Behind the New Kodak Ultima Picture Paper – Beautiful Inkjet Prints that Last for Over 100 Years – Update – May 8, 2004*, Eastman Kodak Company, Rochester, New York. Available as a PDF file from <www.kodak.com>. Together with Kodak's own test data, the articles also include light stability data for Kodak Ultima Picture Paper obtained from ongoing tests conducted by the Image Permanence Institute at the Rochester Institute of Technology (Rochester, New York), and from Torrey Pines Research (Torrey Pines, California). The tests were conducted using the Kodak test procedures and included the use of a UV filter with cool white fluorescent illumination; the Image Permanence Institute and Torrey Pines Research also based print-life calculations on 120 lux for 12 hours per day.

- 3) In typical indoor situations, the "Displayed Prints Framed Under Glass" test condition is considered the single most important of the three display conditions listed. All prints intended for long-term display should be framed under glass or plastic to protect them from staining, image discoloration, and other deterioration caused by prolonged exposure to cigarette smoke, cooking fumes, insect residues, and other airborne contaminants; this precaution applies to traditional silver-halide black-and-white and color photographs, as well as inkjet, dye-sub, and other types of digital prints.
- 4) Displayed prints framed with ultraviolet filtering glass or ultraviolet filtering plastic sheet generally last longer than those framed under ordinary glass. How much longer depends upon the specific print material and the spectral composition of the illuminate, with some ink/paper combinations benefitting a great deal more than others. Some products may even show reduced life when framed under a UV filter because one of the image dyes or pigments is disproportionately pro-

. . . continues next page

# Epson DURABrite Pigment Inks and Epson Photo Paper vs. Store-Brand and Other Non-Genuine, Third-Party Inks and Photo Papers – WIR Print Permanence Ratings<sup>1</sup>

## Notes on These Tests (continued from previous page):

tected from fading caused by UV radiation and this can result in more rapid changes in color balance than occur with the glass-filtered and/or the bare-bulb illumination conditions. For example, if a UV filter protects the cyan and magenta inks much more than it protects the yellow ink in a particular ink/media combination, the color balance of the image may shift toward blue more rapidly than it does when a glass filter is used (in which case the fading rates of the cyan, magenta, and yellow dyes or pigments are more balanced in the neutral scale). Keep in mind, however, that the major cause of fading with most digital and traditional color prints in indoor display conditions is visible light and although a UV filter may slow fading, it will not stop it. For the display permanence data reported here, Acrylite OP-3 acrylic sheet, a “museum quality” UV filter supplied by Cyro Industries, was used.

- 5) Illumination from bare-bulb fluorescent lamps (with no glass or plastic sheet between the lamps and prints) contains significant UV emissions at 313nm and 365nm which, with most print materials, increases the rate of fading compared with fluorescent illumination filtered by ordinary glass (which absorbs UV radiation with wavelengths below about 330nm). Some print materials are affected greatly by UV radiation in the 313–365nm region, and others very little.

“Gas fading” is another potential problem when prints are displayed unframed, such as when they are attached to kitchen refrigerator doors with magnets, pinned to office walls, or displayed inside of fluorescent illuminated glass display cases in schools, stores, and offices. Field experience has shown that, as a class of media, microporous “instant dry” papers used with dye-based inkjet inks can be very vulnerable to gas fading when displayed unframed and/or stored exposed to the open atmosphere where even very low levels of ozone and certain other air pollutants are present. Resistance to ozone exposure varies considerably, depending on the specific type and brand of dye-based inks and photo paper. In some locations, displayed unframed prints made with certain types of microporous papers and dye-based inks have suffered from extremely rapid image deterioration. This type of premature ink fading is not caused by exposure to light. Polluted outdoor air is the source of most ozone found indoors in homes, offices and public buildings. Ozone can also be generated indoors by electrical equipment such as electrostatic air filters (“electronic dust precipitators”) that may be part of heating and air conditioning systems in homes, office buildings, restaurants, and other public buildings to remove dust, tobacco smoke, etc. Electro-

static air filtration units are also supplied as small “tabletop” devices. Potentially harmful pollutants may be found in combustion products from gas stoves; in addition, microscopic droplets of cooking oil and grease in cooking fumes can damage unframed prints. Because of the wide range of environmental conditions in which prints may be displayed or stored, the data given here will be limited by the “Unprotected Resistance to Ozone” ratings. That is, when ozone resistance tests are complete, in cases where the “Unprotected Resistance to Ozone” predictions are less than the “Display Permanence Ratings” for displayed prints that are NOT framed under glass (or plastic), and are therefore exposed to circulating ambient air, the “Display Permanence Ratings” will be reduced to the same number of years given for “Unprotected Resistance to Ozone” even though the “Display Permanence Rating” for unframed prints displayed in ozone-free air is higher. For all of the reasons cited above, all prints made with microporous papers and dye-based inks should always be displayed framed under glass or plastic. For that matter, ALL displayed prints, regardless of the technology with which they are made, should be framed under glass or plastic sheets. This includes silver-halide black-and-white and color prints, dye-sub prints, and inkjet prints made with dye-based or pigmented inks on swellable or microporous papers, canvas, or other materials.

- 6) Prints stored in the dark may suffer slow deterioration that is manifested in yellowing of the print paper, image fading, changes in color balance, and physical embrittlement, cracking, and/or delamination of the image layer. These types of deterioration may affect the paper support, the image layer, or both. Each type of print material (ink/paper combination) has its own intrinsic dark storage stability characteristics; some are far more stable than others. Rates of deterioration are influenced by temperature and relative humidity; high temperatures and/or high relative humidity exacerbate the problems. Long-term dark storage stability is determined using Arrhenius accelerated dark storage stability tests that employ a series of elevated temperatures (e.g., 57°C, 64°C, 71°C, and 78°C) at a constant relative humidity of 50% RH to permit extrapolation to ambient room temperatures (or other conditions such those found in sub-zero, humidity-controlled cold storage preservation facilities). Because many types of inkjet inks, especially those employing pigments instead of dyes, are exceedingly stable when stored in the dark, the eventual life of prints made with these inks may be limited by the instability of the paper support, and not by the inks themselves.

. . . . continues next page

# Epson DURABrite Pigment Inks and Epson Photo Paper vs. Store-Brand and Other Non-Genuine, Third-Party Inks and Photo Papers – WIR Print Permanence Ratings<sup>1</sup>

## Notes on These Tests (continued from previous page):

Due to this concern, as a matter of policy, Wilhelm Imaging Research does not provide a Display Permanence Rating of greater than 100 years for any inkjet or other photographic print material unless it has also been evaluated with Arrhenius dark storage tests and the data indicate that the print can indeed last longer than 100 years without noticeable deterioration when stored at 73°F (23°C) and 50% RH. Arrhenius dark storage data are also necessary to assess the physical and image stability of a print material when it is stored in an album, portfolio box, or other dark place. The Arrhenius data given here are only applicable when prints are protected from the open atmosphere; that is, they are stored in closed boxes, placed in albums within protective plastic sleeves, or framed under glass or high-quality acrylic sheet. If prints are stored, displayed without glass or plastic, or otherwise exposed to the open atmosphere, low-level air pollutants may cause significant paper yellowing within a relatively short period of time. Note that these Arrhenius dark storage data are for storage at 50% RH; depending on the specific type of paper and ink, storage at higher relative humidities (e.g., 70% RH) could produce significantly higher rates of paper yellowing and/or other types of physical deterioration.

7) Tests for “Unprotected Resistance to Ozone” are conducted with an accelerated ozone exposure test using a SATRA/Hampden Test Equipment Ltd. Model 903 Automatic Ozone Test Cabinet (with the test chamber maintained at 23°C and 60% RH) and the reporting method outlined in: Kazuhiko Kitamura, Yasuhiro Oki, Hidemasa Kanada, and Hiroko Hayashi (Seiko Epson), “A Study of Fading Property Indoors Without Glass Frame from an Ozone Accelerated Test,” *Final Program and Proceedings – IS&T’s NIP19: International Conference on Digital Printing Technologies*, sponsored by the Society for Imaging Science and Technology, New Orleans, Louisiana, September 28 – October 3, 2003, pp. 415–419.

WIR test methods for ozone resistance are described in: Michael Berger and Henry Wilhelm, “Evaluating the Ozone Resistance of Inkjet Prints: Comparisons Between Two Types of Accelerated Ozone Tests and Ambient Air Exposure in a Home,” *Final Program and Proceedings: IS&T’s NIP20 International Conference on Digital Printing Technologies*, pp. 740–745, sponsored by the Society for Imaging Science and Technology, Salt Lake City, Utah, November 2004. The IS&T article is also available in PDF format from <www.wilhelm-research.com> <WIR\_IST\_2004\_11\_MB\_HW.pdf>.

8) Changes in image color and density, and/or image diffusion (“image bleeding”), that may take place over time when prints are stored and/or displayed in condi-

tions of high relative humidity are evaluated using a humidity-fastness test maintained at 86°F (30°C) and 80% RH. Depending on the particular ink/media combination, slow humidity-induced changes may occur at much lower humidities – even at 50–60% RH. Test methods for resistance to high humidity and related test methods for evaluating “short-term color drift” in inkjet prints have been under development since 1996 by Mark McCormick-Goodhart and Henry Wilhelm at Wilhelm Imaging Research, Inc. See: Mark McCormick-Goodhart and Henry Wilhelm, “New Test Methods for Evaluating the Humidity-Fastness of Inkjet Prints,” *Proceedings of “Japan Hardcopy 2005” – The Annual Conference of the Imaging Society of Japan*, Tokyo, Japan, June 9, 2005, pp. 95–98. Available in PDF format from <www.wilhelm-research.com> <WIR\_JapanHardcopy2005MMG\_HW.pdf>

See also, Henry Wilhelm and Mark McCormick-Goodhart, “An Overview of the Permanence of Inkjet Prints Compared with Traditional Color Prints,” *Final Program and Proceedings – IS&T’s Eleventh International Symposium on Photofinishing Technologies*, sponsored by the Society for Imaging Science and Technology, Las Vegas, Nevada, January 30 – February 1, 2000, pp. 34–39. See also: Mark McCormick-Goodhart and Henry Wilhelm, “Humidity-Induced Color Changes and Ink Migration Effects in Inkjet Photographs in Real-World Environmental Conditions,” *Final Program and Proceedings – IS&T’s NIP16: International Conference on Digital Printing Technologies*, sponsored by the Society for Imaging Science and Technology, Vancouver, B.C., Canada, October 15–20, 2000, pp. 74–77.

See also: Mark McCormick-Goodhart and Henry Wilhelm, “The Influence of Relative Humidity on Short-Term Color Drift in Inkjet Prints,” *Final Program and Proceedings – IS&T’s NIP17: International Conference on Digital Printing Technologies*, sponsored by the Society for Imaging Science and Technology, Ft. Lauderdale, Florida, September 30 – October 5, 2001, pp. 179–185; and: Mark McCormick-Goodhart and Henry Wilhelm, “The Correlation of Line Quality Degradation With Color Changes in Inkjet Prints Exposed to High Relative Humidity,” *Final Program and Proceedings – IS&T’s NIP19: International Conference on Digital Printing Technologies*, sponsored by the Society for Imaging Science and Technology, New Orleans, Louisiana, September 28 – October 3, 2003, pp. 420–425.

9) Data from waterfastness tests are reported in terms of three subjective classes: “high,” “moderate,” and “low.” Both “water drip” tests and “standing water droplets/gentle wipe” tests are employed.

10) Fluorescent brighteners (also called “UV brighteners,” “optical brighteners,” or

. . . continues next page

# Epson DURABrite Pigment Inks and Epson Photo Paper vs. Store-Brand and Other Non-Genuine, Third-Party Inks and Photo Papers – WIR Print Permanence Ratings<sup>1</sup>

## Notes on These Tests (continued from previous page):

“optical brightening agents” [OBA’s]) are white or colorless compounds added to the image-side coatings of many inkjet papers – and nearly all “plain papers” – to make them appear whiter and “brighter” than they really are. Fluorescent brighteners absorb ultraviolet (UV) radiation, causing the brighteners to fluoresce (emit light) in the visible region, especially in the blue portion of the spectrum. Fluorescent brighteners can lose activity – partially or completely – as a result of exposure to light. Brighteners may also lose activity when subjected to high temperatures in accelerated thermal aging tests and, it may be assumed, in long-term storage in albums or other dark places under normal room temperature conditions. With loss of brightener activity, papers will appear to have yellowed and to be “less bright” and “less white.” In recent years, traditional chromogenic (“silver-halide”) color photographic papers have been made with UV-absorbing interlayers and overcoats and this prevents brighteners that might be present in the base paper from being activated by UV radiation. It is the relative UV component in the viewing illumination that determines the perceived “brightening effect” produced by fluorescent brighteners. If the illumination contains no UV radiation (for example, if a UV filter is used in framing a print), fluorescent brighteners are not activated and, comparatively speaking, the paper appears to be somewhat yellowed – and not as “white.” This spectral dependency of fluorescent brighteners makes papers containing such brighteners look different depending on the illumination conditions. For example, prints displayed near windows are illuminated with direct or indirect daylight, which contains a relatively high UV component, and if an inkjet paper contains brighteners, this causes the brighteners to strongly fluoresce. When the same print is displayed under incandescent tungsten illumination, which has a low UV component, the brighteners have little effect. Another potential drawback of brighteners is that brightener degradation products may themselves be a source of yellowish stain. These problems can be avoided by not adding fluorescent brighteners to inkjet photographic papers during manufacture. When long-term image permanence is of critical importance – with museum fine art collections, for example – papers with fluorescent brighteners should be avoided where possible.

- 11) Although the waterfastness of the color image itself is very high with this paper, the absorbent paper base itself may become cockled, curled, and physically distorted after contact with water. For this reason, the waterfastness of this paper/ink combination is listed as “moderate.”